

TOMAMINE® M-4210

DESCRIPTION

TOMAMINE® M-4210 is an alkyl ether amine-based collector specifically developed for reverse silica flotation from iron ores. It is used in the flotation beneficiation of low-grade hematite-geotite and itaberrite ores.

BENEFITS

- Efficient reverse flotation collector for removal of quartz and silica minerals from various ores
- Low pour point
- Especially suited for flotation of fine silica from hematite ores
- Quick flotation kinetics

APPLICATIONS

- Reverse flotation of iron ore
- Reverse flotation of phosphate ores
- Flotation of glass sands and mica

HANDLING PRECAUTIONS

Please refer to our material safety data sheet for information concerning

- Classification and labelling according to regulations for transport and for dangerous substances
- Protective measures for storage and handling
- Measures in case of accidents and fire
- Toxicity and ecological efficient

RECOMMENDED USAGE

The TOMAMINE® M-4210 typically applied in a 1-4% solution at a dosage range of 0.05 to 0.30lb amine per ton of ore. It may also be partially neutralized with acetic acid to aid in solubility. Use level can best be determined in consultation with our team of applications chemists. Please contact our sales manager or technical expert.

STORAGE AND HANDLING

Keep in closed or covered containers when not in use. Store in cool, dry place with adequate ventilation. Do not store near heat or open flame. For additional storage and handling information, please refer to the material safety data sheet.

PACKAGING

TOMAMINE® M-4210 is available in 55-gallon drums or in bulk in isotainers, tank wagons or tank cars.

PROPERTIES¹

Appearance	Yellow Liquid
Relative Density @ 25°C	0.88
Viscosity @ 24°C (mPas)	28
Flash Point °C	>93
% Neutralization	0

¹ These are typical properties only and do not represent sales or manufacturing specifications.

Disclaimer

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

® = registered trademark ©2019 Evonik Corporation.

Evonik Corporation
Richmond B&I Center
7801 Whitepine Road
Richmond, VA 23237
 PHONE 1 804-727-0700

MiningSurfactants@evonik.com
 www.Mining-Surfactants.com